



Product Data

Castrol Braycote® Micronic 601 EF

Grease, Rust Preventive, Rocket Propellant
Compatible, Low Temperatures

Description

Castrol Braycote® Micronic 601 EF is a smooth, buttery, translucent, off-white, NLGI #2 grease. Its base oil (Castrol Brayco® 815Z) is a perfluorinated polyether, with exceptional chemical resistance, extremely low volatility, and a wide temperature service range. The grease is non-toxic, nonflammable, and does not use any chlorofluorocarbons (CFC's) during product manufacture. This product exhibits unusually high load-carrying capabilities as measured by the Four-Ball EP Test, and contains a rust and corrosion inhibitor for extra component protection. Castrol Fluoroclean™ X100 or Castrol Fluoroclean™ HE can be used to remove this lubricant. Refer to the data sheets for information regarding these products.

Temperature Range

-80°C to 204°C (-112°F to 400°F)

Uses

Castrol Braycote® Micronic 601 EF is designed to operate in the presence of rocket fuels, oxidizers and high vacuum. It is frequently used in space applications including the Space Shuttle and satellites. It should also be considered in any application where a hostile chemical or extreme environmental conditions would preclude the use of an ordinary grease. Typical applications include ball and roller bearings, gears, and as an assembly lubricant for O-rings and elastomers. Perfluorinated greases, such as , this product, exhibit excellent shelf life due to their intrinsic inertness.

Limitations

Castrol Braycote® Micronic 601 EF is compatible with most commonly utilized materials, plastics, and elastomers. It may be adversely affected by Lewis Acid Catalysts such as Aluminum Chloride, at elevated temperatures. Newly exposed rubbing surfaces of aluminum, magnesium and titanium alloys may react with this product under certain conditions. Such systems should be thoroughly evaluated. Surfaces must be well cleaned of organic rust inhibitors prior to grease application to insure proper lubrication. This product is not recommended for use in applications under high vacuum with loads exceeding 100,000 psi for extended periods of time.

Packaging

Castrol Braycote® Micronic 601 EF is available in 2 oz and 4 oz (AVDP) disposable polypropylene syringes and 1 pound jars.

Endurance Technology
1100 West 31st Street
Downers Grove, IL 60515
Tel.: (800) 636 5823
Fax: (630) 241 4140

CASTROL BRAYCOTE® MICRONIC 601EF

TYPICAL PROPERTIES

TEST METHOD	DESCRIPTION	RESULT
D 1403	Penetration @ 25°C (77°F), mm ⁻¹	
	Unworked	285
	Worked, 60 strokes	286
FTM 321	Oil Separation, 30 hrs @ 204°C (400°F), % wt	11.1
	Evaporation Loss, % wt	0.62
D 1743	Rust Prevention	1,1,1, Pass
FTM 5309	Copper Strip Corrosion, 24 hrs @ 100°C (212°F)	1b
D 2266	Four-Ball Wear-Test, AWSD, mm 1200 rpm, 40 kgf load, 1 hr, 75°C (167°F)	0.91
D 2265	Dropping Point, °C (°F)	213 (415)
D 2596	Four-Ball Extreme-Pressure Weld, kgf	800+
E 595 NASA SP-R-0022A	Vacuum Stability Test	
	24 hrs, 125°C (257°F), 10 ⁻⁶ torr	
	Total Weight Loss (TWL), % wt	0.36
	Volatile Condensable Material (VCM), % wt	0.03
D 1478	Low Temperature Torque, g.cm	
	@ -62°C (-80°F)	
	Starting	585
	Running, 1 hr	228
	@ -73°C (-100°F)	
	Starting	1430
	Running, 1 hr	637
D 2512 (MSFC 106)	LOX Impact Sensitivity	
	20 drops, 1100 mm	Pass
D 2595	Evaporation Loss, % wt, 22 hrs, 204°C (400°F)	0.87
FTM 3005 Particles	Micron Range	
	25 - 74 microns	116
	75 microns or larger	None
	Pounds per gallon @ 16°C (60°F)	16.17
	Grams per milliliter @ 16°C (60°F)	1.94
Base Oil Characteristics:		
D 287	Specific Gravity @ 16/16°C (60/60°F)	1.8531
	Pounds per Gallon @ 16°C (60°F)	15.430
D 445	Kinematic Viscosity, cSt	
	@ 99°C (210°F)	45
	@ 38°C (100°F)	148
	@ -54°C (-65°F)	10,855
D 2270	Viscosity Index	350
D 97	Pour Point, °C (°F)	-72 (-100)
Knudsen	Vapor Pressure, torr	
	@ 20°C (68°F)	4 x 10 ⁻¹³
	@ 100°C (212°F)	2 x 10 ⁻⁹
	@ 200°C (392°F)	2 x 10 ⁻⁶

Health, safety and environmental information are provided for this product in the Materials Safety Data Sheet. This gives details of potential hazards, precautions and First Aid measures, together with environmental effects and disposal of used products. Castrol will not accept liability if the product is used other than in the manner or with the precautions or for the purpose(s) specified. Before using the product other than directed, please contact Castrol for consultation.